

Duncan

METALLIC glazes

Tips & Techniques



- For full coverage, apply 3 to 4 flowing coats, letting dry between coats.
- Fire these glazes to shelf cone 04. **Antique Pewter** (1st glaze shown) fires to cone 06.
- Do not fire Duncan Metallics with greenware or other glazes (underglazes like Concepts are okay). The greenware fumes can damage the glaze, and other glazes may turn the Metallics **black**.
- Projects painted with Metallic Glazes should **not** be dipped before firing.
- Apply color in a crosshatch pattern to minimize brush marks.