



Phone: 574-333-2249  
 Phone: 844-202-2537  
 Email: info@worldcellextrusions.com

1741 Conant St.  
 Elkhart, IN  
 46516

## Typical Properties

**Item name:** WC-29-3-48-96-BU

**Item Description:** 29lb Worldcell, 3mm x 48 x 96, blue

Test	Test Method	Unit of Measure	Result
Thickness		mm	3
Density		kg/m <sup>3</sup>	460
		lb/ft <sup>3</sup>	29
Weight Per Area		GSM	1380
		oz/yd <sup>2</sup>	41
Impact Strength	ASTMD5628-10	Joules	2.4
Flexural Strength (MD)	ASTM D790-10	Mpa	14
Flexural Strength (TD)	ASTM D790-10	Mpa	13
Flexural Modulus (MD)	ASTM D790-10	Mpa	520
Flexural Modulus (TD)	ASTM D790-10	Mpa	470
Flammability	FMVSS302 / CMVSS302	Pass/Fail	Pass
Working Temperature Range		Fahrenheit	-20° to 180°
		Celsius	-30° to 80°

MD = Machine Direction

TD = Transverse Direction

### Standard Tolerance:

Thickness	+/- 0.15mm
Width	-0, +1/4"
Length	-0, +1"
Density	+/- 10%